

PP HTR KT 001 Filaments

Technical Data sheet

rev. 1



DESCRIPTION

PP HTR KT 001 is 3D Printing Filament in polypropylene with Mineral Filler and Thermal Stability additive.
Only Black.

APPLICATIONS

3D Printing Prototyping Technologies

Property Test Condition	Standard	Unit	Values 50%RH
Mechanical Properties			
Izod Impact, Notched (23°C)	ASTM D 256/A	J/m	140
Flexural Modulus	ASTM D 790	MPa	8600
Thermal Properties			
H.D.T. Method A (1,80 MPa)	ASTM D 648	°C	150
Other Properties			
Density	ISO 1183	g/cc	1,15
Fire Resistance (3,2 mm)	UL 94		HB
Processing			
Melt Temperature Range		°C	190 - 230

PP HTR KT 001 Filaments

Technical Data sheet



SUPPLY FORM

PP HTR KT 001 is supplied as Filaments. It has to be kept in its original packaging.

HAZARD AND HANDLING PRECAUTIONS

PP HTR KT 001 is Polypropylene resin, under normal conditions of use, should pose no unusual problems from incidental ingestion, or eye and skin contact. However, caution is advised when handling, storing, using, or disposing of these resins, and good housekeeping and controlling of dusts are necessary for safe handling of product. Workers should be protected from the possibility of contact with molten resin during fabrication. Handling and fabrication of resins can result in the generation of vapours and dusts that may cause irritation to eyes and the upper respiratory tract. In dusty atmospheres, use an approved dust respirator. Pellets or beads may present a slipping hazard. Good general ventilation of the polymer processing area is recommended. At temperatures exceeding the polymer melt temperature (typically 200°C), polymer can release fumes, which may contain fragments of the polymer, creating a potential to irritate eyes and mucous membranes. Good general ventilation should be sufficient for most conditions.

PROCESSING

PP HTR KT 001 Filaments can be processed by all conventional 3D printing techniques. Heat Bed 100°C. Mass temperature can be less as 300°C..

DISPOSAL

DO NOT DUMP INTO ANY SEWERS, ON THE GROUND, OR INTO ANY BODY OF WATER. For unused or uncontaminated material, the preferred options include recycling into the process or sending to an industrial composting facility, if available; otherwise, send to an incinerator or other thermal destruction device. For used or contaminated material, the disposal options remain the same, although additional evaluation is required. All disposal methods must be in compliance with Federal, State/Provincial, and local laws and regulations.

DISCLAIMER

The above information is provided in good faith. Keytech is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, PP HTR KT 001 MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.